



THE PROFESSIONAL'S CHOICE SINCE 1974

December 3, 2015

Tomomi Yadomura
Purchasing Department Import
Yamachi Corporation

Re: Information on Non-combustibility

Dear Tomomi,

Below is the material information for the non-combustibility testing.

			Composition of Dried Materials					
			Organic		Inorganic			
	Thick-	Dried				Calcium		
	ness	Weight	Acrylic	Other*	Coarse	Carbonate		
	[mm]	[kg/m ²]	Polymer	additives	Aggregate	Fillers	Talc	Cement
StyroGlue	1.6	3.0	10%			30%		60%
AkroFlex Primer	0.1	0.14	20%	3%		58%	19%	
MultiTex	1.5	1.9	10%	3%	30%	57%		
SemiSmooth	1.5	1.9	10%	3%	46%	41%		
Malibu 16	2	1.8	10%	3%	60%	27%		
CircleTex Coarse	3	2.7	10%	3%	64%	23%		

^{* (}Titanium Dioxide, Propylene Glycol, etc)

Sincerely,

OMEGA PRODUCTS INTERNATIONAL

Kevin Wensel

Director of Product Development

2. 20

DISCLAIMER:

Omega and its employee's, agents or contracted representatives are not certified inspectors. This report is provided in good faith only. Omega disclaims all liability for errors or omissions in this report or any other report or site visit by Omega's employees, agents or contracted representatives. Furthermore, Omega disclaims any verbal recommendations, direction or instructions and any liability for such. Omega disclaims all liability for the installation and application of Omega's products. This report WILL NOT provide assurance of proper application of Omega's products and systems or any other product or system on this or any other project. Omega is not supervising or inspecting the installation and application of our products or systems or any other product or system on this job or any other job. It is the applicators sole responsibility to insure proper and complete product application.